

EasyGloss

Product description

Type

This is a high quality alkyd topcoat.

Features and benefits

It has a high gloss finish with very good levelling characteristics. It has excellent gloss and colour retention. It is easy to apply. It is fast drying. It has very good hiding power.

Recommended use

To be used as a topcoat for aggressive atmospheric exposure.

Packaging (typical)

	Volume (litres)	Size of containers (litres)
EasyGloss 2.5L: white colour only	0.75 / 2.5	0.75 / 2.5

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

Product data

Colours	selected range of colours		
Generic type	alkyd		
Solids	39 ± 2 volume%		
Flash point	35 °C		
VOC for Ready-for-Use Mixture	EU limit value for this product (cat. A/d): 400 g/l (2007). This product contains max 480 g/l VOC.		
VOC	490	g/l	US EPA method 24
VOC-Solvent Emission Directive	4,1	g/kg	SED (1999/13/EC)

Application data

The product can be applied by

Brush: Use a suitable brush. Care must be taken to achieve the specified dry film thickness.

Roller: Use a suitable roller. Care must be taken to achieve the specified dry film thickness.

Spreading rate per coat

Theoretical 13 - 7,8 m²/l

Recommended film thickness per coat

Wet 75 - 130 μm
Dry 30 - 50 μm

Product mixing ratio (by volume)

Single pack

Thinner

Jotun Thinner No. 2

Drying times

Drying and curing times are determined under controlled temperatures and relative humidity below 85%, and at the typical DFT for the product.

Substrate temperature	5 °C	10 °C	23 °C	40 °C
Surface (touch) dry	6 h	4 h	2 h	1 h
Hard dry	18 h	12 h	6 h	4 h
Dry to over coat, minimum	32 h	24 h	14 h	10 h

Directions for use

Surface preparation

Surfaces with grease, oil or other contamination, wash with recommended Jotun Yachting detergent. High pressure fresh water washing followed by sanding with P280-P360 is necessary. For best result, the substrate should be clean, dry and free from any contamination.

Primer

Refer to TDS, direction for use for the selected Jotun Yachting product.

Filler

Refer to TDS, direction for use for the selected Jotun Yachting product.

Finish coat

Apply two coats.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 23 °C

EasyGloss 48 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Disclaimer

The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.