



# Hybrid Fabric

## TEXTILE DATA SHEET

**G. Angeloni** reference

**GDc 210 T2 Blue**

CHARACTERISTICS	
Mass per unit area	g/m <sup>2</sup>
Weave	
Standard Width	mm
Laminate thickness	mm
Other informations	

Nominal	Tolerance	Normative
<b>206</b>	± 5%	ISO 4605
2x2 Twill		ISO 2113
1000	± 2,5%	
<b>0,21</b>	± 15%	ISO 5084(**)
Loomstate		

Nominal Construction	
Fibre description	
Thread Count	ends/cm
Weight distribution	g/m <sup>2</sup>
	%
Weight Rate	%

WARP		WEFT	
3K carbon fiber 200 tex		Blue Polyester 1100 dtex	
<b>4,80</b>	ISO 4602	<b>10,00</b>	ISO 4602
3K carbon fiber 200 tex	<b>96</b>	Blue Polyester 1100 dtex	<b>110</b>
	47%		53%
47%		53%	

(\*\*) Theoretical thickness for an epoxy laminate with 40% of reinforcement in volume.

Date of Issue	28/08/2012	No. of Pages	1
---------------	------------	--------------	---

Note : Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.



**G. Angeloni srl**

via Abate Tommaso , 72/A5 - 30020 Quarto d'Altino (VE) - ITALY

Tel. +39 0422 823801 - 780580 Fax +39 0422 782782

E-Mail : info@g-angeloni.com