

# CRYSTIC<sup>®</sup> VE679-03PA

## DCPD - Modified Vinyl Ester Resin for Infusion

### Introduction

Crystic VE 679-03PA is a pre-accelerated, DCPD modified, vinyl ester resin.

### Applications

Crystic VE 679-03PA was developed for use as a infusion resin with a wide range of gel times with various catalysts.

### Features & Benefits

Crystic VE 679-03PA has excellent blister resistance and significantly reduces the occurrence of print through, to produce durable mouldings with an enhanced surface finish.

### Product Characteristics

#### FORMULATION

Crystic VE 679-03PA must be thoroughly stirred and allowed to attain workshop temperature (18 °C – 20 °C) before use. It needs only the addition of a catalyst to start the curing reaction. The recommended catalyst is Trigonox 249, which should be added at 2 % into the resin. The geltime of Crystic VE 679- 03PA can be approximately determined from the table below.

### Pot Life

Temperature	Pot Life in Minutes Using 2% Trigonox 249
15°C	195 minutes
20°C	120 minutes
25°C	80 minutes

The resin, mould and workshop should be at, or above, 15°C before curing is carried out.

### Additives

The addition of pigment, fillers or other additives may adversely affect the resin properties. Users should consult Scott Bader's Technical Service Department before making any such additions.

### Typical Properties

The following tables give typical properties of Crystic VE 679-03PA when tested in accordance with the appropriate BS or BS EN ISO test method.

Property		Liquid Resin
Appearance		Red/ Brown
Viscosity at 25°C 4500sec-1	Poise	1.7 / 2.0
Specific Gravity @ 25°C		1.065
Stability in the dark at 25°C	Months	3
Geltime at 25°C using 2 % Trigonox 249	Minutes	80

Property		Fully Cured Resin (unfilled casting)	
		*	**
Barcol Hardness (GYZJ 934 - 1)		22	34
Deflection Temperature under load (1.80 MPa) †	°C	58	97
Tensile Strength	MPa	53	64
Tensile Modulus	GPa	4.9	3.35
Elongation at Break	%	2.27	2.27

\* Curing Schedule - 24hrs @ 20 °C, 16hrs @ 40 °C

\*\* Curing Schedule - 24hrs @ 20 °C, 3hrs @ 80 °C

† Curing Schedule - 24hrs @ 20 °C, 5 hrs @ 80 °C, 3 hrs @ 120 °C

### Storage

Crystic VE 679-03PA should be stored in the dark in suitable closed containers. It is recommended that the storage temperature should be less than 20 °C where practical, but should not exceed 30 °C. Ideally, containers should be opened only immediately prior to use.

### Packaging

Crystic VE 679-03PA is supplied in 25kg and 200kg steel containers.

### Health & Safety

Please see separate Materials Safety Data Sheet.

Version 2: May 2014

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

### SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

[www.scottbader.com](http://www.scottbader.com)