

HJSIL® 200

Hydrophilic fumed silica

Characteristics

HJSIL® 200 is a kind of hydrophilic fumed silica with a specific surface area of 200 m²/g. It's high purity white colloidal powder.

Applications

- HTV and RTV silicone rubber
- Adhesives and sealants
- Paints, coatings and pigments
- Printing inks
- Cable compounds
- Unsaturated polyester resins, laminated resins and Gel coats

Packaging and storage

HJSIL® 200 is supplied in 10kg kraft paper bags. We recommend to store the product in closed containers under dry conditions and to protect the material from volatile substances.

Properties

- Reinforcement filler in elastomers
- Rheology and thixotropy control of liquid systems, binders, polymers, etc.
- Used as anti-settling, thickening, anti-sagging agent
- Improvement of free flow and anti-caking characteristics of powders
- High transparency

Characteristic physico-chemical data

Properties and test methods	Unit	Typical Value	Standardization
Specific surface area (BET)	m ² /g	200 ± 25	GB/T10722
pH value (in 4% dispersion)		3.6 ~ 4.5	GB/T1717
Loss on drying (2 hours at 105 °C)	Wt%	≤ 1.5	GB/T5211.3
Loss on ignition (2 hours at 1000 °C, based on material dried for 2 hours at 105 °C)	Wt%	≤ 2.5	GB/T20020
Sieve residue (45 μm)	%	≤ 0.025	GB/T5211. 14
Silica content (based on ignited material)	Wt%	≥ 99.8	GB/T20020
Tamped density (based on material dried for 2 hours at 105 °C)	g/L	40 ~ 60	GB/T5211.4
Carbon content (based on material dried for 2 hours at 105 °C)	Wt%	≤ 0.2	GB/T20020

Contact information

HENAN MINMETALS EAST INDUSTRIAL Co., Ltd.

Address RENMIN ROAD, JIAOZUO CITY,
HENAN PROVINCE, 454000
CHINA

Tel +86 391 3565627

Fax +86 391 3565657

Email info@minmetalseast.com

Internet www.minmetalseast.com

The data presented in this document is based on our best knowledge. We disclaim any warranty and liability whatsoever as to accuracy and completeness of such information as well as to the potential infringement of any proprietary rights. We reserve the right to alter product constants within the scope of technical progress or new developments. Any user of our products shall bear the full risk connected to their use including but not limited to their properties and fitness for any purpose.