Duratec® Polyester Duratec Surface Primer



The ultimate High-Gloss surface primer for wood,
MDF, tooling board and composite plugs, patterns and models. Unique air-cure technology for fast cure even with thin coats. Easy to sand, polish to a gloss.
Take a mold directly off the Surface Primer or topcoat for the highest gloss.

Recommended Uses:

- Surface coat for plugs/ patterns for composite tooling.
- Easy Sanding High-Build Primer for composite parts.
- High Build, Fast Sanding Primer perfectly smooth surfaces

Recommended Uses: (cont)

- A substitute for sanding gelcoat - epoxy laminates or pinhole-free surfaces.
- Highly crosslinked coating providing excellent chemical resistance

Features:


Low Porosity- provides a super fine leveling and filling system. Applied properly, Surface Primer provides a porosity-free surface without pinholes or defects.

Adhesion to most epoxies- with heat distortion level of 200° F/93 C the primer also adheres to fiberglass, wood, MDF, brick, concrete and polyurethane foam.

Rapid Buildup- up to 40 mils 1000 micorns, wet on wet, on composite plugs and master mold surfaces. Save time and labor.

Easy Sanding-also saves time and labor. The primer cures to a surface that polishes to a gloss.

707-002 Dark Grey





Hawkeye Industries

P..O..Box.415, Bloomington, CA.92316 (USA).800-977-0060.•.(Outside.USA).909-546-1160.•.Fax.909-546-1161 Email:.hawkeyesales@hawkeyeind.com •.www.duratec1.com



707-002 Dark Grey

Data Sheet Continued

Duratec® Polyester Surface Primer

Page: 2

Product Properties:

Viscosity as measured on a Brookfield Visometer Model RFG, Spindle #5 at 2.5 rpm	2300-2600 cps
Thixotropic	5
Gel Time: Sample based upon a 100 g mass, catalyzed with 2% Norox 925	
Weight per Gallon	10.9 lb, 4.995 kg.
Coverage per Gallon:	
10 mil thickness (wet-dry)	160 ft²-125 ft²
250 micron thickness (wet-dry)	15 m²-12 m²

Use Instructions:

- Mix thoroughly with a drill-mounted mixer or paint shaker. Hand stirring is not enough.
- Duratec Surface Primer is designed to be applied when the ambient temperature and part temperature are both above 60°F.
- Catalyze with 1.75-2.25% MEKP Catalyst. Norox 925 works well. Mix well.
- Surface Primer can be applied by roller, brush or by spray. Spray with an HVLP gun, or with a gelcoat application system. Seek a fine spray, and use the lowest pressure that allows an even spray fan. (approximately 40 psi).
 A 2.0 mm tip is recommended.
- Apply at least 10 mils for even and complete cure. Recoat before the Primer has set up and lost its tack. If the Primer cures completely wait at least eight hours, sand, and recoat.
- Additional solvent is not needed for most spray guns. If solvent is required, do not add Acetone or Styrene.
- Duratec Thinner is the best choice. Methyl Ethyl Ketone Solvent will work for most users. High quality urethane reducers are good choices. Lacquer Thinners are not recommended.
- Sand when the primer has cured. Start with the finest paper that will remove the surface profile. If sprayed well, 220 or 320 grit paper is a good starting point.
- Wait at least eight hours from the start of sanding before polishing or topcoating.
- Agua Buff 1000 and 2000 are good choices for compounding and polishing Surface Primer.
- Duratec Pot Life Extender will extend the pot life by 2-3 times, and does not extend the cure time (spray only).

Revised 11-19-15



Hawkeye Industries

P.O.Box.415,.Bloomington,.CA.92316 (USA).800-977-0060.•.(Outside.USA).909-546-1160.•.Fax.909-546-1161 Email:.hawkeyesales@hawkeyeind.com www.duratec1.com

Limited/ warranty statement: Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special, incidental or consequential damages.